


**KPH 66-116 (106AT5,106BT5,106BT6, 106BT7)****Application:** Transparent hose**Description:** This compound is based on the most transparent stabilizer and high-quality plasticizers. Final product has glossy, shimmering surface.**106AT5** is approximately odorless and based on highly effective lubricant.**Packaging:** 25 kg laminated polypropylene bags**Storage:** dry place, away from the sun, temperature below 30°C**Color:** Transparent (These grades can have blue and white undertones)

Properties	Unit	Amount	Standard
Density	$gr/cm^3$	1.16±0.01	ASTM D 792
Hardness at 15 second	Shore "A"	66±2	ASTM D 2240
Thermal stability at 200°C	Minute	80±5	VDE 0472
Mechanical properties Tensile Elongation	MPa %	9±1 Min 300	ASTM D 638

Temperature profile:

The recommended temperature settings for the extruder with L/D around 22-24 are as follows :

	Zone 1	Zone 2	Zone 3	Zone 4	Head	Die
Temp (°C)	135±5	140±5	145±5	150±5	145±5	155±5

**Head Office:** 5<sup>th</sup> floor, Number 51, 6<sup>th</sup> Golestan street, Pasdaran Avenue, Tehran, Iran. Tel : (+98 21)79453000, Fax: (+98 21)88762819[info@khorramco.com](mailto:info@khorramco.com) website: [www.khorramco.com](http://www.khorramco.com)

Approved by : QC &amp; Laboratory Manager