



KPF 8267 (131CCZP1- 131CCZ1)


Application: This compound is designed based on special stabilizers and is used as a filler in the field of wires and cables.

Description: Light filler

Packaging: 25 kg laminated polypropylene bags

Storage: dry place, away from the sun, temperature below 30°c

Color: 131CCZ1 white and 131CCZP1 black



Properties	Unit	Amount	Standard
Density	gr/cm^3	1.67 ± 0.01	ASTM D 792
Hardness at 15 second	Shore "A"	82 ± 2	ASTM D 2240
Thermal stability at 200°c	Minute	Min 60	VDE 0472
Mechanical properties Tensile Elongation	MPa %	7 ± 1 150 ± 20	IEC 60811-1-1

Temperature profile:

The recommended temperature settings for the extruder with L/D around 22-24 are as follows :

	Zone 1	Zone 2	Zone 3	Zone 4	Head	Die
Temp (°C)	140-160	150-170	160-180	170-190	160-180	180-195

Head Office: 5th floor, Number 51, 6th Golestan street, Pasdaran Avenue, Tehran, Iran. Tel : (+98 21)79453000, Fax: (+98 21)88762819

info@khorramco.com website: www.khorramco.com

Approved by : QC & Laboratory Manager