



**KPM 8525 (129ACZ)**

**Application:** Transparent-Flexible wrap (Medical)

**Description:** This compound is based on the transparent stabilizer and high-quality plasticizers. This grade provides requirements of medical based productions and offers high level of sealing.

**Packaging:** 25 kg laminated polypropylene bags

**Storage:** dry place, away from the sun, temperature below 30°C

**Color:** Transparent (These grades can have blue and white undertones)



Properties	Unit	Amount	Standard
Density	gr/cm <sup>3</sup>	1.25 ± 0.01	ASTM D 792
Hardness at 15 second	Shore "A"	85 ± 2	ASTM D 2240
Thermal stability at 200°C	Minute	Min 30	VDE 0472
Mechanical properties Tensile Elongation	MPa %	Min 19 Min 210	ASTM D 638

Temperature profile:

The recommended temperature settings for the extruder with L/D around 22-24 are as follows :

	Zone 1	Zone 2	Zone 3	Zone 4	Head	Die
Temp (°C)	140-160	150-170	160-180	170-190	160-180	180-195

**Head Office:** 5<sup>th</sup> floor, Number 51, 6<sup>th</sup> Golestan street, Pasdaran Avenue, Tehran, Iran. Tel : (+98 21)79453000, Fax: (+98 21)88762819

[info@khorramco.com](mailto:info@khorramco.com) website: [www.khorramco.com](http://www.khorramco.com)

Approved by : QC & Laboratory Manager