

مركبات الأحذية

نعل الحذاء

- الشفافية القابلة للتبديل
- حقن صب الصف
- المرونة المطلوبة

NO	Compound Type	Product Grade	Code	Color	Density (gr/cm ³)	Hardness (Shore" A")	Heat Stability at 200°C	Tensile Strength (N/mm ²)	Elongation at Break (%)
1	Semi-Transparent Shoesole	104ABL	500120	Semi-Transparent	1/16±0/01	62±2	50 min	10±1	min 320
2	Semi-Transparent Shoesole- Economical	104BBL	500017						
3	Semi-Transparent Shoesole	106ABL	500122	Semi-Transparent	1/17±0/01	66±2	50 min	12±1	min 300
4	Semi-Transparent Shoesole- Economical	106 BBL	500973						
5	Semi-Transparent Shoesole	108ABL		Semi-Transparent	1/18±0/01	70±2	60 min	12±1	min 290
6	Semi-Transparent Shoesole- Economical	108BBL		Semi-Transparent					
7	Transparent- Semi rigid	129BT5		Transparent	1/21±0/01	82±2	70 min	18±1	min 210
8	Foam	108CBLF	500118	white- grey	0/6±0/01	68±2	



Address:
5th floor, No. 51, Golestan 6,
Pasdaran St, Tehran, Iran

Website:
www.khorramco.com
info@khorramco.com

Phone:
(+98) 21 79453000

