

PACKAGING

-  Desirable transparency
-  High thermal stability
-  Favorable processability

بسته بندی

-  شفافیت مطلوب
-  پایداری حرارتی بالا
-  فرایند پذیری مناسب



NO	Compound Type	Product Grade	Code	Color	Density (gr/cm ³)	Hardness (Shore" A,D")	Heat Stability at 200°C	Tensile Strength (N/mm ²)	Elongation at Break (%)
1	Transparent- impact modified- bottle	168AT51	500318	Transparent	1.31	75±1D	60	20±1	20
2		168AT52	500319						
3		168AT53	500780		1.29	75±1D	60	20±1	20
4	Shrink packaging	168AT5 017	500679						
5	Film Stretch	129BT5 001	500226		1.21	82±2A	70min	18±1	min 210
6		129BT5 015	500553						
7	Medical Wrap	129ACZ 1	500652		1.25	85±2A	35min	min 19	min 210

